

TEST REPORT



APPLICANT : HYUNDAI L&C

REPORT NO. : D270-20-01315

SAMPLE RECEIVED DATE : 2020-11-11

REPORT ISSUED DATE : 2020-12-16

PAGE : 1 OF 3

=====

SAMPLE NAME SUBMITTED BY THE APPLICANT : BODAQ PLATE

=====

TEST CONDUCTED : As requested by the applicant, for details please see attached page(s).

=====

PREPARED AND CHECKED BY
FOR FITI



GANG WEON, JEUNG
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



JE-GOO JUN
PRESIDENT

※ Report Verification No.: GNGR-QMZK-XZRH ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.
This test report is irrelevant to KS Q ISO/IEC 17025 and KOLAS accreditation.

**01. DETERMINATION RESISTANCE OF SYNTHETIC POLYMERIC MATERIAL TO FUNGI
(ASTM G21 - 15) : RATE**

	#1
	0

NOTE) · RATE : 0 = NONE

1 = TRACE OF GROWTH (LESS THAN 10 %)

2 = LIGHT GROWTH (10 TO 30 %)


3 = MEDIUM GROWTH (30 TO 60 %)

4 = HEAVY GROWTH (60 % TO COMPLATE COVERAGE)

- TEST ORGANISM : *Aspergillus brasiliensis* ATCC 9642
Chaetomium globosum ATCC 6205
Penicillium funiculosum ATCC 11797
Trichoderma virens ATCC 9645
Aureobasidium pullulans ATCC 15233

· SEE ATTACHED PHOTOS


**** End of The Report ****



e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KS Q ISO/IEC 17025 and KOLAS accreditation.

- DETERMINATION RESISTANCE OF SYNTHETIC POLYMERIC MATERIAL TO FUNGI PHOTO : VIABILITY -



- DETERMINATION RESISTANCE OF SYNTHETIC POLYMERIC MATERIAL TO FUNGI PHOTO : #1 -



e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.

This test report is irrelevant to KS Q ISO/IEC 17025 and KOLAS accreditation.